

Performance Benefits and Overview

UD05 – Desiccant Masterbatch contains: Calcium oxide, resin and some additives. It's suitable for blowing film and injection molding, extrusion. The purpose use this grade to remove humidity inside plastic, resistance fish eyes, reduce engraver for dryer, time dry.

CaO Content	75 %
Carrier Resin	LLDPE
Melt Mass- Flow Rate (190°C/2.16kgs)	0.8 g/10 mins
Melt Temperature	110°C
Humidity	<0.15 wt %
Bulk Density	0 g/cm ³
Processing Temperature	140-200°C

Main Features

Good Dispersion	✓
Gloss Finish	✓
Food Contact	✓
Good Processability	✓
High Light Fastness	✓
Excellent Heat Resistance	✓
Increase Hardness	✓

Depending on processing parameters or local specifications. It is advisable to check with our sales to commercial production.

UD05	Polymer Compatibility			
	LLDPE	HDPE	LDPE	PP
	✓	✓	✓	✓

Standard Packaging	Certificate
25 kg bags (pallet 1350kg) Jumbo Bag (1200 kg)	FDA, REACH, ISO 1900-2015

Main Application	Properties	Dosage
Blow Film (Roll bags, T-shirt bags, Garbage bags)		Upto 5 %
Blow Molding (HDPE pipes, Bottles, Containers, Cans)		Upto 5 %
Extrusion		

The product should be stored in dry conditions at temperatures below 25°C protected from direct sunlight. If these protective measures are not taken into account impairment of the product is possible. This can result in degradation of the color, smell or loss of other properties. The data and information contained are presented in good faith, and are based on USMASTERBATCH's current knowledge and experience. They are provided for guidance only. Because many factors may affect processing or application/use of the product, USMASTERBATCH recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to us.

FOR & ON BEHALF OF

US MASTERBATCH JOINT STOCK COMPANY